

CARBO 0/14


Péetrographie : CALCAIRE DUR VISEEN

Annule et remplace la FTP du 11 juillet 2022

SCALPAGE TRAITE A 1% DE CHAUX CL90-Q (R5,P2)

Résultats de production

| | jusqu'au 22/12/22 | | | | | | | | | | | | | | | | | |
|---------------------|-------------------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|--------|--------|-------|-------|
| | 0.063 | 0.08 | 0.125 | 0.25 | 0.5 | 1 | 2 | 4 | 5 | 6.3 | 8 | 10 | 12.5 | 14 | 16 | 20 | MB | VBS |
| Maximum | 13.91 | 14.60 | 17.12 | 20.15 | 22.48 | 28.80 | 43.80 | 55.57 | 63.97 | 78.88 | 91.06 | 98.14 | 99.57 | 99.83 | 100.00 | 100.00 | 3.80 | 0.16 |
| Xt+1.25xEcart-types | 10.97 | 11.49 | 13.53 | 17.00 | 21.24 | 28.24 | 40.35 | 55.46 | 62.99 | 72.73 | 81.91 | 90.57 | 96.30 | 98.61 | 100.00 | 100.00 | 2.69 | 0.12 |
| Moyenne Xf | 7.92 | 8.27 | 9.86 | 12.58 | 16.12 | 21.53 | 30.75 | 43.73 | 50.76 | 58.76 | 70.14 | 80.68 | 90.01 | 92.99 | 95.73 | 99.67 | 1.49 | 0.07 |
| Xt-1.25xEcart-types | 4.87 | 5.06 | 6.20 | 8.17 | 11.00 | 14.82 | 21.14 | 31.99 | 38.53 | 44.79 | 58.38 | 70.79 | 83.73 | 87.37 | 90.99 | 98.68 | 0.30 | 0.02 |
| Minimum | 4.75 | 4.97 | 5.97 | 7.48 | 9.72 | 11.61 | 15.14 | 24.45 | 31.05 | 34.12 | 53.38 | 68.51 | 84.18 | 87.62 | 89.78 | 97.33 | 0.40 | 0.02 |
| Ecart-type | 2.440 | 2.575 | 2.930 | 3.533 | 4.097 | 5.370 | 7.685 | 9.386 | 9.784 | 11.179 | 9.411 | 7.910 | 5.030 | 4.498 | 3.793 | 0.790 | 0.954 | 0.043 |
| Nombre de résultats | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 | 15 |



WIL 11.07.00.61-2 (c) Arcade 1996,2022

le Responsable Laboratoire

E. COLIN