

0/14 R

Péetrographie : CALCAIRE DUR VISEEN  
Elaboration : TERTIAIRE

Annule et remplace la FTP du 12 juillet 2023


Partie contractuelle  
Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire		Norme	Code
0	14	NF EN 13285 Graves non traitées	GNT4 (19/10/2004)

	0.063	0.08	0.125	0.25	0.5	1	2	4	5	6.3	8	10	12.5	14	16	20	28	31.5	MB	VBS	MDE	LA	LA+MDE
Etendue e	5				10	15	15	15			15			10		2		0					
Incertitude U	2				2	4	4	4			3			2		1		0	0.5				
V.S.S.+U	11.0				24	37	45	58			75			99		100		100	3.00				
V.S.S.	9.0				22	33	41	54			72			97		100		100	2.50	0.10	25	30	45
V.S.I.	4.0				12	18	26	39			57			87		98		100					
V.S.I.-U	2.0				10	14	22	35			54			85		97		100					
Ecart-type max	1.52				3.03	4.55	4.55	4.55			4.55			3.03		0.61		0.00					
Xr	7.5				18	25	36	48			67			95		100		100					

Partie informative  
Résultats de production

	du 08/02/23 au 20/12/23																				du 17/07/23 au 18/12/23		
	0.063	0.08	0.125	0.25	0.5	1	2	4	5	6.3	8	10	12.5	14	16	20	28	31.5	MB	VBS	MDE	LA	LA+MDE
Maximum	9.0	10.0	12	17	21	29	41	52	57	63	72	81	92	97	100	100	100	100	1.60	0.06	12	22	34
Xt+1.25xEcart-types	8.8	9.6	12	16	21	28	40	52	57	63	71	80	91	96	100	100	100	100	1.10	0.05			
Moyenne Xt	7.9	8.5	10	14	19	25	36	47	52	58	67	76	89	95	100	100	100	100	0.58	0.03	10	20	30
Xt-1.25xEcart-types	6.9	7.4	9	12	16	22	31	42	47	53	63	73	87	93	99	100	100	100	0.06	0.01			
Minimum	6.8	7.4	9	12	16	21	29	41	46	51	62	72	86	93	99	100	100	100	0.20	0.01	7	19	27
Ecart-type	0.76	0.88	1.1	1.5	1.8	2.5	3.6	4.2	4.2	3.9	3.0	2.6	1.8	1.2	0.3	0.0	0.0	0.0	0.413	0.015	2.0	1.0	2.0
Nombre de résultats	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	8	8	8



le Responsable Laboratoire

E. COLIN



Adresses sur quefairedemesdechets.fr